## UNITED STATES PATENT AND TRADEMARK OFFICE CERTIFICATE OF CORRECTION

PATENT NO. : 7,331,372 B2 Page 1 of 2

APPLICATION NO.: 10/549429
DATED: February 19, 2008
INVENTOR(S): Kiyoto Takizawa et al.

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Column 13, line 20, to Column 14, line 29, delete claims 6 through 12, and insert the following claims 6 through 12 reordered:

- --6. The method for melting a metallic raw material in a metal molding apparatus according to claim 1, wherein said melting cylinder is made of a metallic material having a linear expansion coefficient smaller than a linear expansion coefficient of said metallic raw material.
- 7. The method for melting a metallic raw material in a metal molding apparatus according to claim 3, wherein a heating means is provided within said auxiliary heating member and the center portion of said cylindrical metallic raw material is directly heated from a bottom surface thereof by contact between said auxiliary heating member and the bottom surface of said cylindrical metallic raw material.
- 8. The method for melting a metallic raw material in a metal molding apparatus according to claim 4, wherein a heating means is provided within said auxiliary heating member and the center portion of said cylindrical metallic raw material is directly heated from a bottom surface thereof by contact between said auxiliary heating member and the bottom surface of said cylindrical metallic raw material.
- 9. The method for melting a metallic raw material in a metal molding apparatus according to any one of claims 1 to 8, wherein said metallic raw material is made of a low melting metal alloy selected from the group consisting of:

a magnesium alloy, and an aluminum alloy.

## UNITED STATES PATENT AND TRADEMARK OFFICE CERTIFICATE OF CORRECTION

PATENT NO. : 7,331,372 B2 Page 2 of 2

APPLICATION NO.: 10/549429
DATED: February 19, 2008
INVENTOR(S): Kiyoto Takizawa et al.

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

- 10. The method for melting a metallic raw material in a metal molding apparatus according to claim 9, wherein said metallic raw material is composed of a magnesium alloy exhibiting thixotropic properties at a temperature in a solid-liquid coexisting temperature range.
- 11. The method for melting a metallic raw material in a metal molding apparatus according to claim 9, wherein the melting of said metallic raw material is performed after cutting and removing cavities generated in a surface layer of the cylindrical metallic raw material and impurities adhered to a surface of the material.
- 12. The method for melting a metallic raw material in a metal molding apparatus according to claim 10, wherein the melting of said metallic raw material is performed after cutting and removing cavities generated in a surface layer of the cylindrical metallic raw material and impurities adhered to a surface of the material.--

Signed and Sealed this

Eleventh Day of August, 2009

Varid J. Kappos

David J. Kappos

Director of the United States Patent and Trademark Office